

TEST REPORT

COMPANY NAME: MECDEX
ADDRESS LIBERMANN International
 P.O Box-1166 Harrar, Wazirabad
 Road, Sialkot-51310, Pakistan
EMAIL: ali.anwar@libermann.com
ATTN: Ali Anwar
TEL: +92 52 3252201-2
FAX: +92 52 3252208

Report No.: FTL-423/101019
TRF No.: FTL-423/101019
Date In: 10th Oct 2019
Date Out: 17th Oct 2019
No. Of Working Days: 07 Days
Page: 1 of 4
Pretest for Buyer Not Listed

Sample Description:	Active Skin Gloves
Color(s):	Grey/Black/Yellow
Lab Id Color(S):	Grey/Black/Yellow
P.O. No(s):	Not Listed
Article No(s):	DY -813
Season:	Not Listed
Quantity Submitted:	10 Pairs
Country of Origin:	Pakistan
Country of Destination:	Europe
Dept:	Not Listed
End Use:	Not Listed

Submitted Fiber Content:	Not Listed
Multi Layers	Silicon Printed Synthetic Leather + 3D Mesh Fabric + Lightweight Stretchable Spandex Fabric
Test Requested:	EN 388: 2016 + A1: 2018, EN 420: 2003 + A1: 2009
Submitted Care Instruction:	Not Listed
Suggested Care Instruction:	Not Listed

If Retest

Previous Report No.:	Not Listed
-----------------------------	------------

If Revision

Reason For Revision	Not Listed
----------------------------	------------

PHOTO OF THE SUBMITTED SAMPLE



Require Tests & Detail

Test Name:

Abrasion Resistance
Blade Cut
Tear Resistance
Puncture Resistance
Sizing
Dexterity

EN 388: 2016 + A1: 2018
EN 388: 2016 + A1: 2018
EN 388: 2016 + A1: 2018
EN 388: 2016 + A1: 2018
BS EN 420: 2003 + A1: 2009
BS EN 420: 2003 + A1: 2009

**FIRST TESTING LAB
AUTHORIZED SIGNATORIES**


Test Conducted by


Test Checked by


Approved By

Please Contact:

For any Technical Issues: Mr. Rehan Qamar

Tel: +92 52 3252201 – 05

Fax: +92 52 3252208

Email: lab@nizamsons.com , lab@libermann.com

SUMMARY OF TEST RESULTS

TEST PROPERTY	Standard Method	Results	Comments
ABRASION RESISTANCE	EN 388: 2016 + A1: 2018	Level-3	
BLADE CUT RESISTANCE	EN 388: 2016 + A1: 2018	Level-1	
TEAR RESISTANCE	EN 388: 2016 + A1: 2018	Level-4	
PUNCTURE RESISTANCE	EN 388: 2016 + A1: 2018	Level-2	
SIZING	BS EN 420: 2003 + A1: 2009	Pass	
DEXTERITY	BS EN 420: 2003 + A1: 2009	N/A	


Parameter	EN 388: 2016 + A1: 2018	Test Requirement	Test Results	Remarks										
Abrasion Resistance (Cycles) Tested – Palm Portion Used abradant: Klingspor PL 31 B	Clause 6.1	<table border="1"> <thead> <tr> <th>Level of Performance</th> <th>Number of Cycles</th> </tr> </thead> <tbody> <tr> <td>1</td> <td>100</td> </tr> <tr> <td>2</td> <td>500</td> </tr> <tr> <td>3</td> <td>2000</td> </tr> <tr> <td>4</td> <td>8000</td> </tr> </tbody> </table>	Level of Performance	Number of Cycles	1	100	2	500	3	2000	4	8000	5000 Cycles	Compiles with Level - 3
		Level of Performance	Number of Cycles											
		1	100											
		2	500											
		3	2000											
4	8000													
<table border="1"> <thead> <tr> <th>Level of Performance</th> <th>Index (i)</th> </tr> </thead> <tbody> <tr> <td>1</td> <td>≥ 1.2</td> </tr> <tr> <td>2</td> <td>≥ 2.5</td> </tr> <tr> <td>3</td> <td>≥ 5.0</td> </tr> <tr> <td>4</td> <td>≥ 10.0</td> </tr> <tr> <td>5</td> <td>≥ 20.0</td> </tr> </tbody> </table>	Level of Performance	Index (i)	1	≥ 1.2	2	≥ 2.5	3	≥ 5.0	4	≥ 10.0	5	≥ 20.0	> 1.2 & < 2.5 Index	Level-1
Level of Performance	Index (i)													
1	≥ 1.2													
2	≥ 2.5													
3	≥ 5.0													
4	≥ 10.0													
5	≥ 20.0													
<table border="1"> <thead> <tr> <th>Level of Performance</th> <th>Strength (N)</th> </tr> </thead> <tbody> <tr> <td>1</td> <td>10</td> </tr> <tr> <td>2</td> <td>25</td> </tr> <tr> <td>3</td> <td>50</td> </tr> <tr> <td>4</td> <td>75</td> </tr> </tbody> </table>	Level of Performance	Strength (N)	1	10	2	25	3	50	4	75	> 75 Newton	Level-4		
Level of Performance	Strength (N)													
1	10													
2	25													
3	50													
4	75													
<table border="1"> <thead> <tr> <th>Level of Performance</th> <th>Strength (N)</th> </tr> </thead> <tbody> <tr> <td>1</td> <td>20</td> </tr> <tr> <td>2</td> <td>60</td> </tr> <tr> <td>3</td> <td>100</td> </tr> <tr> <td>4</td> <td>150</td> </tr> </tbody> </table>	Level of Performance	Strength (N)	1	20	2	60	3	100	4	150	> 60 & < 100 Newton	Level-2		
Level of Performance	Strength (N)													
1	20													
2	60													
3	100													
4	150													
<table border="1"> <thead> <tr> <th>Level of Performance</th> <th>Strength (N)</th> </tr> </thead> <tbody> <tr> <td>1</td> <td>10</td> </tr> <tr> <td>2</td> <td>25</td> </tr> <tr> <td>3</td> <td>50</td> </tr> <tr> <td>4</td> <td>75</td> </tr> </tbody> </table>	Level of Performance	Strength (N)	1	10	2	25	3	50	4	75	> 75 Newton	Level-4		
Level of Performance	Strength (N)													
1	10													
2	25													
3	50													
4	75													
<table border="1"> <thead> <tr> <th>Level of Performance</th> <th>Strength (N)</th> </tr> </thead> <tbody> <tr> <td>1</td> <td>10</td> </tr> <tr> <td>2</td> <td>25</td> </tr> <tr> <td>3</td> <td>50</td> </tr> <tr> <td>4</td> <td>75</td> </tr> </tbody> </table>	Level of Performance	Strength (N)	1	10	2	25	3	50	4	75	> 75 Newton	Level-4		
Level of Performance	Strength (N)													
1	10													
2	25													
3	50													
4	75													

The specified performance levels are valid for only the palm area of this glove.

Parameter	EN 420: 2003 + A1: 2009	Test Requirement	Test Results	Remarks
Sizing in millimeters (mm)	Clause 5.1	Size	Lab Analysis	PASS
		Submitted Size: Small, Medium, Large, X-Large, XX-Large, XXX-Large	<u>Small</u> Circumference- 202 Size 7 <u>Medium</u> Circumference- 227 Size 8 <u>Large</u> Circumference- 238 Size 9 <u>X-Large</u> Circumference- 254 Size 10 <u>XX-Large</u> Circumference- 266 Size 11 <u>XXX-Large</u> Circumference- 280 Size 11	
Dexterity in millimeters (mm)	Clause 5.2	Level of Performance	Test is Not Applicable	N/A
		Diameter of Pins (mm)		
		1		
		2		
		3		
		4		
		5		

The above specified results are valid for only this glove model.

EN 388



3 1 4 2 X

“End of Report”